DIAION[™] WA30C

DIAION™ WA30C is a highly porous type weakly basic anion exchange resin. It is has tertiary amine functionality and low-leachable properties compared with DIAION™ WA30. A wide range of applications, especially in a field of higher purity water treatment application, is recommended.

		-	
Рr	· ^	А	 ct

Product			
Grade Name	DIAION [™] WA30C		
Туре	Weak Base Anion		
Matrix	Styrene-DVB, Highly Porous		
Functional Group		Tertiary Amine	
Ionic Form		Free Base	
Specification			
Whole Bead Count	-	95 min.	
Total Exchange Capacity	meq/mL	1.5 min.	
Water Content	%	43 - 55	
Particle Size Distribution on 1180 μm	%	5 max.	
Particle Size Distribution thr. 300 μm	%	1 max.	
Effective Size	mm	0.40 min.	
Uniformity Coefficient	-	1.6 max.	
COD	ppm	5 max.	
Typical Properties			
Shipping Density	g/L	650	
Mean Particle Size	μm	700	
Particle Density	g/mL	1.05	
Total Swelling (FB to Cl ⁻)	%	23	
Recommended Operating Conditions	5		
Maximum Operating Temperature	°C	100	
Operating pH Range		0 - 9	
Minimum Bed Depth	mm	800	
Service Flow Rate	m/h	10 - 40	
Regenerant		NaOH	
Regenerant Concentration	%	NaOH 1 - 4	



Regenerant Level

Regenerant Flow Rate

Total Rinse Requirement



% of ionic load

m/h

BV



120

2 - 6

5 - 10

DIAION[™] WA30C

Hydraulic Characteristics

The approximate pressure drop at various temperatures and flow rates for each meter of bed depth of DIAIONTM WA30C resin in normal down flow operation is shown in the graphs below.




Fig. 1 Pressure Drop of WA30C




Fig. 2 Bed Expansion of WA30C

Notice

DIAIONTM is a registered trademark of Mitsubishi Chemical Corporation. The information contained herein is believed to be true and accurate, but all data, recommendations and suggestions are provided without guarantee, since the conditions of use are beyond our control and can affect the performance and properties of our products. The user is solely responsible for confirming that our product is suitable for the intended end use, and for compliance with all legal regulations and patents. Other than compliance with published Mitsubishi Chemical Corporation specifications agreed to pursuant to a signed writing during the warranty period, and except as required by law, MITSUBISHI CHEMICAL CORPORATION AND ITS AFFLIATES MAKE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If a product is found to be defective during the warranty period, user's sole remedy and our sole obligation is, at our option, replacement of the affected product or refund of the purchase price. Except as required by law, we are not liable for any damage, harm or loss resulting from our product, whether direct, indirect, consequential, incidental or special, and irrespective of legal theory asserted, including strict liability, contract, warranty, or negligence.





